

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

EK

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 4/60, 10/00	A1	(11) International Publication Number: WO 96/23005 (43) International Publication Date: 1 August 1996 (01.08.96)
<p>(21) International Application Number: PCT/US96/00644</p> <p>(22) International Filing Date: 2 January 1996 (02.01.96)</p> <p>(30) Priority Data: 08/378,202 25 January 1995 (25.01.95) US 08/544,051 17 October 1995 (17.10.95) US</p> <p>(71) Applicant: W.R. GRACE & CO.-CONN. [US/US]; 1114 Avenue of the Americas, New York, NY 10036 (US).</p> <p>(72) Inventors: WARD, David, George; 8408 Woodland Manor Drive, Laurel, MD 20724 (US). CARNAHAN, Edmund, Malott; Apartment No. 302, 5635 Columbia Road, Columbia, MD 21044 (US).</p> <p>(74) Agent: CAPRIA, Mary, Ann; W.R. Grace & Co.-Conn., 7500 Grace Drive, Columbia, MD 21044 (US).</p>	<p>(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AZ, BY, KZ, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	
<p>(54) Title: A SUPPORTED CATALYTIC ACTIVATOR</p> <p>(57) Abstract</p> <p>A supported polyolefin catalyst activator, comprising a four coordinate anion having a direct chemical bond to a catalyst carrier, wherein said anion is comprised of a neutral, three coordinate compound, MR_3, and a carrier having oxygen containing functionalities, wherein M is selected from the group comprising boron, tellurium, aluminum, gallium, indium and mixtures thereof, and R's can be the same or different and are selected from the group comprising alkyls, alkoxys, alkenyls, halogen substituted alkyls, alkoxys, and alkenyls, aryls, aryl halides, halides and mixtures thereof; and a cation counter ion to said anion, wherein said cation is a protonated base or a Lewis Acid capable of protonating or abstracting a moiety, such as an alkyl or aryl, from a transition metal containing catalyst precursor resulting in a cationic transition metal species.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

A SUPPORTED CATALYTIC ACTIVATOR

This application is a continuation-in-part of U.S. Patent No. 08/378,202, filed January 25, 1995.

5 Field of Invention

The invention relates to catalyst activator compositions, to a method for preparing such catalyst activator compositions, to a method of using such catalyst activator and to polymer products produced with such
10 catalyst compositions using the present activator. More particularly, this invention relates to compositions, comprising supported ionic catalyst activator compositions useful to activate polyolefin catalysts to polymerize olefins, diolefins and/or acetylenically unsaturated
15 monomers to homopolymer, copolymer and terpolymer products.

Background Of The Invention

Ziegler-Natta (Z-N) and metallocene-alumoxane type
20 catalyst systems for the polymerization of olefins are well known in the art. Recently a new, ionic pair type of catalyst has been developed which yields polymers of improved properties compared to those made with conventional catalyst systems.

25 These systems typically use Group IV-B metallocene catalysts prepared as a reaction product of a Group IV-B metal metallocene compound and an ionic activator compound. U.S. Patent No. 5,241,025 teaches the use of a catalyst system comprising a Group III-A element compound
30 comprising a cation capable of donating a proton which will irreversibly react with at least one ligand contained in the Group IV-B metal compound and an anion which is

- 2 -

bulky, labile and non-coordinatable with the Group IV transition metal cation produced upon the reaction of the metallocene and activator compound. Similarly, U.S. Patent No. 5,198,401 teaches that ionic catalyst compositions can be prepared by combining two components, bis(cyclopentadieny) Group IV-B metal complex containing at least one ligand which will combine irreversibly with the second component or at least a portion thereof such as a cation portion thereof. The combination of the two components produces an ionic catalyst composition comprising a cationic bis(cyclopentadienyl) Group IV-B metal complex which has a formal coordination number 3 and a 4+ valence charge and the aforementioned non-coordinating anion. Both of these U.S. Patents are directed to homogenous metallocene polyolefin catalyst systems. Use of these catalyst systems in other reactor designs, particularly slurry reactors, can result in reactor fouling, poor productivities, poor polymer bulk densities, and poor polymer particle morphologies. For these reasons, it is desirable to develop heterogeneous versions of these ion pair cocatalysts, where the cocatalyst is deposited on a carrier, preferably an oxide such as silica or alumina.

An example of a supported ion pair catalyst system is taught in WO 94/03506, wherein a support which had been modified with an alkyl aluminum reagent is treated with a solution of a metallocene catalyst and an anionic activator, and the solvent is removed. The resulting catalyst system provided a low activity heterogeneous ion pair catalyst system. Because there is no direct chemical bond between the catalyst ion pair and the support,

- 3 -

resolubilization of the catalyst may make this system unsuitable for slurry reactors.

WO 93/11172 discloses the use of certain polyanionic transition metal catalyst compositions wherein the polyanionic moiety comprises a plurality of metal or metalloid atoms - containing non-coordinating anionic groups pendant from and chemically bonded to a core component through use of a carbon containing a spacer between the metal or metalloid atoms and the core component. However, WO 93/11172 teaches to avoid exposing its activator to high concentrations of functionalities which are known poison for metallocene polymerization catalysts and in fact, teaches the necessity of masking reactive functionalities on a support, such as hydroxyl-groups on silica.

The present invention overcomes the above mentioned problems and provides further improvements to catalytic systems by providing a catalyst activator chemically bound directly to the support, reducing resolubilization of heterogeneous catalysts and therefore minimizing reactor fouling. Furthermore, the present invention further permits the use of supports having high concentrations of chemical functionalities that would otherwise act as poisons to metallocene catalysts.

In addition, the direct bond between the support and the catalyst activator provides a large support effect, allowing properties of the activator to be altered by modifying the support and consequently, permitting the support to influence the polymer morphology.

Furthermore, catalyst systems containing the present activator produce a high bulk density polyethylene. The high bulk products cost less to ship to end users, flow

- 4 -

better in molding operations and eliminates the need to pelletize what would otherwise have been a resin fluff.

Additionally, multi-modal polyolefin resins may be prepared using the supported catalytic activator of the present invention with a mixture of catalysts, including
5 chromium, Ziegler-Natta and metallocene catalysts.

- 5 -

Summary Of The Invention

The present invention meets the above objectives by providing an improved supported catalyst activator. The invention further provides unique catalyst activator compositions suitable for use with multiple catalysts, permitting the support to influence polymer morphology and reducing fouling of polymerization equipment.

The present invention is directed to a supported catalyst activator comprising a four coordinate anion species having a direct chemical bond to a catalyst carrier wherein said anion species is comprised of a neutral three coordinate compound, MR_3 , and a support having oxygen containing functionalities, wherein the M is selected from the group consisting of boron, tellurium, aluminum, gallium and indium and mixtures thereof and the R's may be identical or different and are selected from the group consisting of alkyls, halogen substituted alkyls, aryls, arylhalides, alkenyls, alkoxy and halides and mixtures thereof; and a cation to this anion wherein said cation is a protonated base or a Lewis Acid, including hydrogen cation, capable of protonating or abstracting a moiety, such as an alkyl, aryl, or halogen moiety, from a transition metal containing catalyst precursor resulting in a cationic transition metal species.


The invention further includes methods of producing the supported catalyst activator and the polymers produced from polymerizing monomers in contact with the resulting catalyst system incorporating the activator of the present invention.

Detailed Description Of The Invention

- 6 -

The present invention is directed to a supported catalyst activator comprising an anion species having a direct chemical bond to a catalyst support having oxygen containing functionalities; wherein said anion species having the general formula MR_x , wherein the M is selected from the group consisting of boron, tellurium, aluminum, gallium and indium and mixtures thereof and the R's are independent and selected from the group consisting of alkyls, alkenyls, halogen substituted alkyls, aryls, arylhalides, alkoxy and halides and may be the same or different; and a cation to this anion wherein said cation is a protonated base or a Lewis Acid, including hydrogen cation, capable of protonating or abstracting a moiety, such as an alkyl, aryl, halogen from a transition metal containing catalyst precursor resulting in a transition metal cation.

One possible structure for this type of species is shown below.



20

Where, $[C]^+$ is an activating cation, which may be a Bronsted acid capable of donating a proton to the transition metal catalytic precursor resulting in a transition metal cation. Such Bronsted acids include but are not limited to ammoniums, oxoniums, phosphoniums and mixtures thereof; preferably ammoniums of methylamine, aniline, dimethylamine, diethylamine, N-methylaniline, diphenylamine, trimethylamine, triethylamine, N,N-dimethylaniline, methyldiphenylamine, pyridine, p-bromo-N,N-dimethylaniline, p-nitro-N,N-dimethylaniline; phosphoniums from triethylphosphine, triphenylphosphine and diphenylphosphine; oxoniums from ethers such as

30

- 7 -

dimethyl ether, diethyl ether, tetrahydrofuran and dioxane; sulfoniums from thioethers such as diethyl thioethers and tetrahydrothiophene; and mixtures of the foregoing; most preferably dimethylanilinium.

5 Furthermore, [C⁺] may be an abstracting moiety that is capable of reacting with a transition metal catalytic precursor resulting in the transition metal cation. Acceptable abstracting moiety include but are not limited to silver, carboniums, tropylium, carbeniums,
10 ferroceniums and mixtures thereof; preferably carboniums and ferroceniums and mixtures thereof; and most preferably triphenyl carbonium. The [C⁺] may also include mixtures of the Bronsted acids and the abstracting moiety species as described herein.

15 R can be the same or independent and are selected from the group comprising halogen (including chlorine, bromine, fluorine, iodine and mixtures thereof, preferably chlorine and fluorine), mono or multi-cyclic (including halosubstituted) aryls, alkyls, and alkenyl
20 compounds and mixtures thereof; preferred are C1-C20 alkenyl groups (such as ethenyl, propylenyl, butenyl, and pentenyl); C1-20 alkyl groups (such as a methyl, ethyl, n-propyl, iso-propyl, n-butyl, n-octyl, and 2-ethylhexyl groups), C6-20 aryl group (including substituted aryls)
25 (such as phenyl, p-tolyl, benzyl, 4-t-butylphenyl, pentafluorophenyl, 2,6 dimethylphenyl, 3,5- methylphenyl, 2,4-dimethylphenyl, 2,3-dimethylphenyl, pentafluorobenzyl groups); C1-C20 alkoxy (such as ethoxy, butoxy, t-butoxy, n-butoxy) and mixtures thereof. More preferred R groups
30 are C1-C5 alkyls, phenyl and naphthyl and mixtures thereof.

- 8 -

M is selected from the group comprising boron, aluminum, gallium, indium, tellurium and mixtures thereof;

O is oxygen; and

Support is a carrier or support defined as
5 inorganic carriers, inorganic oxide carriers, and organic carriers. Of these, inorganic carriers and inorganic oxide carriers are particularly preferably.

Inorganic oxide carriers include SiO_2 , Al_2O_3 , MgO , ZrO_2 , TiO_2 , Fe_2O_3 , B_2O_3 , CaO , ZnO , BaO , ThO_2 and mixtures
10 thereof such as silica alumina, silica alumina titania, zeolite, ferrite and [glass fibers, any O]. In addition, the above-mentioned inorganic oxide carriers may contain a small amount of carbonates, nitrates, sulfides or the like.

15 Additional carrier materials include aluminum phosphate gel materials as well as polymeric or organic supports containing reactive functionalities such as polyvinylalcohol, poly(methylmethacrylate) and hydroxy substituted polystyrene and mixtures of two or more of
20 the foregoing.

Preferred carrier materials are silica or alumina based materials such as oxide of silica, and oxides of Si-Al, Si-Ti, Si-Al-Ti, SiMgCl_2 , and aluminum phosphate gel materials and mixtures thereof; and most preferred
25 materials are silica, Si-Al, Si-Ti, Si-Al-Ti, and SiMgCl_2 materials and mixtures thereof.

The carriers suitable for this invention can be, but need not be calcined before use.

Preferably, the carriers are compositions
30 conventionally used as a catalyst support material. The degree of porosity in the carrier may be any level that is achievable in the starting material. Preferably, the

- 9 -

carrier particles of the present invention have a pore volume of at least 0.3 cc/g; preferably from 0.3 to 5 cc/g; more preferably from 0.3 to 3 cc/g; and most preferably, the pore volume exceeds 1 cc/g. Preferably, the carrier particles have a surface area of about 1-1000 m²/g; preferably from 200 - 800 m²/g ; and most preferably from 250 to 650 m²/g. The typical particle size for a suitable carrier for this invention is from 1 to 300 microns, preferably from 10 to 200 microns, more preferably from 20 to 100 microns.

Pore volume and surface area can be, for example, measured from volume of nitrogen gas adsorbed in accordance with BET method. (Refer to J. Am. Chem. Soc., vol. 60, p. 309 (1983)).

In the preferred embodiments of the present invention, the M is boron, aluminum or mixtures thereof, the support is calcined silica, the R is selected from the group comprising halosubstituted and non-substituted C1-C5 alkyls and C6-C18 aryls and mixtures thereof, and the cation is either an alkyl substituted ammonium salt or mixtures thereof; and preferably are dimethylanilinium, triphenylmethane cation and mixtures thereof.

In a preferred embodiment, the composition is a borate-modified support formed by the interaction of 1) a carrier, having a hydroxyl functionality including but not limited to silicas and aluminas; 2) a three coordinate boron or aluminum species; 3) a base; and 4) a cation that can serve to abstract an alkyl ligand from a metallocene alkyl.

Components 3) and 4) may result from the same chemical or a combination of two or more chemicals. The resulting modified support contains a four-coordinate

- 10 -

anionic species with a direct chemical bond to the support.

Examples of the boron species suitable for use in this invention include but are not limited to

5 tri(phenyl)boron, tri(p-tolyl)boron, tri(o-tolyl)boron, tri(pentafluorophenyl)boron, tri(o,p-dimethylphenyl)boron, tri(m,m-di(trifluoromethyl) phenyl)boron, tri(p-trifluoromethylphenyl)boron, and the like; and mixtures of the foregoing.

10 Examples of the aluminum species suitable for use in this invention include but are not limited to tri(phenyl)aluminum, tri(p-tolyl)aluminum, tri(o-tolyl)aluminum, tri(pentafluorophenyl)aluminum, tri(o,p-dimethylphenyl)aluminum, tri(m,m-

15 di(trifluoromethyl)phenyl)aluminum, tri(p-trifluoromethylphenyl) aluminum, and the like; and mixtures of the foregoing.

Examples of suitable bases for use in this invention is any base capable of deprotonating the carriers, and

20 include, but are not limited to, the following species: metal hydroxides, metal alkyls and aryls, trialkyl-substituted amines such a triethylamine, tripropylamine, tri(n-butyl)amime, trimethylamine, and the like; N,N-dialkyl anilines such as N,N-dimethylaniline, N,N,-

25 diethylaniline, N,N,-2,4,6-pentamethylaniline and the like; dialkyl amines such as di-(isopropyl)amine, dicyclohexylamine and the like; triaryl phosphines such as tri(methylphenyl)phosphine and tri(dimethylphenyl)phosphine and the like; and mixtures of

30 the foregoing.

One method for preparing the present composition comprises:

- 11 -

- 1) treating a catalyst support having the potential for nucleophilic oxygen sites, in an organic solvent, with a C1-C20 metal alkyl, C6-C20 metal aryl, substituted C1-C20 metal alkyls and C6-C20 metal
5 aryls and mixtures thereof; wherein the metal in this reagent is selected from the group comprising Group 1 and 2 metals from the Periodic Table and mixtures thereof; preferably N-butyllithium, dibutylmagnesium, methyllithium, butylmagnesium
10 chloride and mixtures thereof, which can react with the support surface to generate nucleophilic oxygen sites, and
- 2) adding a neutral, three coordinate metal component MR,
15 as defined above, and
- 3) adding an organic compound, which reacts with the product metal component from step 2. Suitable organic compounds include those of the general
20 formula R'X, capable of reacting to form a cation, which in turn reacts with the transition metal catalyst precursor. The R' is selected from the group comprising hydrogen, and halosubstituted and nonsubstituted alkenyl, alkyl, aryl, or arylalkyl
25 radicals having from 1-20 carbon atoms or two carbon atoms joined together to form a part of C4 to C6 ring. X is any halogen, preferably chlorine or bromine. A suitable organic compound includes pronated amides and ammonium salts as well.
30 Preferred organic compounds are a halogen containing compound such as chlorotriphenylmethane,

- 12 -

dimethylanilinium chloride, and mixtures of the foregoing.

The reagents are used in quantities that can be expressed in terms of mmol of reagent to gram of support. In steps 1), 2) and 3) the mmol of the added reagent (i.e., the metal alkyl and aryls, MR_x , and the organic compound respectively) are used in an amount ranging from 0.01-10.00 mmole:gram of support, preferably 0.10-1.0 mmol/gram, and more preferably 0.5mmol:gram of support. Preferably the amount of the reagents used in steps 2) and 3) are equal to or exceed that amount of reagent used in step 1).

Another method for preparing the present invention comprises the following steps which can be carried in any order:

1) treating a catalyst support, preferably in an organic solvent with an organic base in solution, preferably of the formula R_3N wherein N is nitrogen, and the R's are independently selected from the group comprising hydrogen, C1-C20 alkyl (preferably C3-C9), C6-C20 aryls (preferably C8-C14, substituted C1-C20 alkyls (preferably C3-C9) and C6-C20 aryls (preferably C8-C14), and may be the same or different; preferred amines are as dimethylaniline, tributylamine, triethylamine, and mixtures thereof, and

2) adding a neutral material, MR_x , as defined above. The reagents are used in quantities that can be expressed in terms of mmol of reagent to gram of support. In steps 1) and 2) the mmol of the added reagent (i.e., the organic base and MR_x , respectively)

- 13 -

are used in an amount ranging from 0.01-10.00 mmole:gram of support, preferably 0.10-1.0mmol/gram, and more preferably 0.5mmol:gram of support.

5 Preferrably the amount of the reagent used in step 2) is equal to or exceed that amount of reagent used in step 1).

Suitable organic solvents for either of these methods include but are not limited to non-polar organic solvents. 10 Most preferably includes aliphatic hydrocarbons (typically C3 to C12, such as butane, isobutane, pentane, isopentane, hexane, octane, decane, dodecane, hexadecane, octadecane, and the like); alicyclic hydrocarbons (typically C5-C20, such as cyclopentane, 15 methylcyclopentane, cyclohexane, decalin cyclooctane, norbornane, ethylcyclohexane and the like); aromatic hydrocarbons, including substituted aromatics such as benzene, chlorobenzene, xylene, toluene and the like; and petroleum fractions such as gasoline, kerosene, light 20 oils, and the like. It may also be desirable to use tetrahydrofuran or another ether. Mixtures of two or more solvents may also be used, e.g., Exxon's IsoPar ®

Either of these methods further includes the step of removing the solvent from the reaction product by any 25 number of usual techniques, including evaporative and filtering techniques.

PREFERRED CATALYTIC PRECURSORS

30 The active olefin polymerization catalyst is formed by the interaction of the present supported catalytic activator with the transition metal catalyst precursor.

- 14 -

Such transition metal catalyst precursor compounds of the Group IV V, VI metal hydrocarbyloxides as described in WO 92/01006, metallocenes as defined herein, Group IV and other metal monocyclopentadienyl-heteroatom ligand
5 compounds as described in U.S. Patent Nos. 5,005,438; 5,096,867; 5,057,475; and WO 92/12162.

The catalyst activator of the present invention is suitable for use with any polyolefin catalyst system, most preferably metallocene systems, but may also be useful in
10 mixed Ziegler-Natta/Metallocene systems which may optionally include one or more chromium catalysts.

As used herein metallocene is defined as organometallic compounds having a transition metal, including rare earth metals, in coordination with members
15 of at least one five-member carbon ring, heterosubstituted five-member carbon ring, or a bridged (ansa) ligand defined as multi cyclic moieties capable of coordinating to the transition or rare earth metals.


The ansa bridge can be selected from the group
20 comprising carbon, silicon, phosphorus, sulfur, oxygen, nitrogen, germanium, species such as R_2C , R_2Si , R_2Ge , $R'_2CR'_2C$, $R'_2SiR'_2Si$, $R'_2GeR'_2Ge$, $R'_2CR'_2Si$, $R'_2CR'_2Ge$, $R'_2CR'_2CR'_2C$, $R'_2SiR'_2Si$ diradicals where R' is independently selected from the group containing hydride, halogen radicals, and
25 C1-20 hydrocarbyl radicals including ethyl and propyl; preferred ansa bridges are Me_2Si (dimethylsilyl), Ph_2Si (diphenylsilyl), Me_2C (isopropylidene), Ph_2P (diphenylphosphoryl) $Me_2SiSiMe_2$ (tetramethyldisilane) and the like. Preferably, the ansa bridge has a length of
30 two atoms or less as in methylene, ethylene, diphenylsilyl, dimethylsilyl, propylidene and methylphenylsilyl.

- 15 -

The transition metal component of the metallocene is selected from Groups 3 through Group 10, 13-17 of the Periodic Table, lanthanides and actinides and mixtures thereof; preferably Group 3, 14, 15, 16 and lanthanides and actinides metals; and most preferably titanium, zirconium, hafnium, chromium, vanadium, samarium and neodymium. Of these Ti, Zr, and Hf are most preferable.

In one preferred embodiment, the metallocene catalyst is represented by the general formula $(Cp)_mMR^4_nR^5_p$, wherein Cp is a substituted or unsubstituted cyclopentadienyl ring, M is a Group 4, 14, 5, 15, 6 and 16 transition metal; R^4 and R^5 are independently selected halogen, hydrocarbyl group, or hydrocarboxyl groups having 1-20 carbon atoms; $m=1-3$, $p=0-3$ and the sum of $m+n+p$ equals the oxidation state of M.

In another embodiment the metallocene catalyst is represented by the formulas:



Wherein Me is a Group 4, 14, 5, 15, 6 or 16 transition metal; $C_5R^6_m$ is a substituted cyclopentadienyl each R^6 , which can be the same or different is hydrogen, alkenyl, aryl, or arylalkyl radical having from 1 to 20 carbon atoms or two carbon atoms joined together to form a part of a C4 to C6 ring; R^7 is one or more of or a combination of a carbon, a germanium, a silicon, a phosphorous or a nitrogen atom containing radical substitution on and bridging two $C_5R^6_m$ rings or bridging one $C_5R^6_m$ ring back to Me, when $p=0$ and $x=1$ otherwise x is always equal to 0, each K which can be the same or different is an aryl alkyl, alkenyl, alkaryl, or arylalkyl radical having from 1-20 carbon atoms or

- 16 -

halogen, K' is an alkylidene radical having from 1 to 20 carbon atoms, s is 0 to 1 and when s is 0, m is 5 and p is 0, 1, or 2 and when s is 1, m is 4 and p is 1.

The transition metal component of the metallocene is selected from Groups 3 through Group 10, 13 through 17 and lanthanides and actinides of the Periodic Table and mixtures thereof, preferably Group 3, 4, 5, 6 and lanthanides and actinides metals, and most preferably titanium, zirconium, hafnium, chromium, vanadium, samarium and neodymium. Of these Ti, Zr, and Hf are most preferable.

In particular, preferred metallocenes are derivatives of a cyclopentadiene (Cp), including cyclopentadienyl, indenyl, fluorenyl, tetrahydroindenyl, and 1,1-disubstituted silacyclopentadienes, phosphocyclopentadienes, 1-metallocyclopenta-2,4-dienes, bis(indenyl)ethane and mixtures thereof.

Additional illustrative but non-limiting examples of metallocenes represented by the above definition are dialkyl metallocenes such as bis(cyclopentadienyl)titanium dimethyl, bis(cyclopentadienyl)titanium diphenyl, bis(cyclopentadienyl)zirconium dimethyl, bis(cyclopentadienyl)zirconium diphenyl, bis(cyclopentadienyl)hafnium dimethyl and diphenyl, bis(cyclopentadienyl)titanium dineopentyl, bis(cyclopentadienyl)zirconium dineopentyl, bis(cyclopentadienyl)titanium dibenzyl, bis(cyclopentadienyl)zirconium dibenzyl, bis(cyclopentadienyl)vanadium dimethyl; the mono alkyl metallocenes such as bis(cyclopentadienyl)titanium methyl chloride, bis(cyclopentadienyl)titanium ethyl chloride, bis(cyclopentadienyl)titanium

- 17 -

phenyl chloride, bis(cyclopentadienyl)zirconium methyl chloride,
bis(cyclopentadienyl)zirconium ethyl chloride, bis(cyclopentadienyl)zirconium phenyl chloride, bis(cyclopentadienyl) titanium methyl bromide; the trialkyl metallocenes such as cyclopentadienyl titanium trimethyl, cyclopentadienyl zirconium triphenyl, and cyclopentadienyl zirconium trineopentyl, cyclopentadienyl zirconium trimethyl, cyclopentadienyl hafnium triphenyl, cyclopentadienyl hafnium trineopentyl, and cyclopentadienyl hafnium trimethyl; monocyclopentadienyls titanocenes such as, pentamethylcyclopentadienyl titanium trichloride, pentaethylcyclopentadienyl titanium trichloride; bis(pentamethylcyclopentadienyl) titanium diphenyl, the carbene represented by the formula bis(cyclopentadienyl)titanium=CH₂ and derivatives of this reagent; substituted bis(cyclopentadienyl)titanium (IV) compounds such as: bis(indenyl)titanium diphenyl or dichloride, bis(methylcyclopentadienyl)titanium diphenyl or dihalides; dialkyl, tri-alkyl, tetra-alkyl and penta-alkyl cyclopentadienyl titanium compounds such as bis(1,2-dimethylcyclopentadienyl)titanium diphenyl or dichloride, bis(1,2-diethylcyclopentadienyl)titanium diphenyl or dichloride; silicon, phosphine, amine or carbon bridged cyclopentadiene complexes, such as dimethyl silyldicyclopentadienyl titanium diphenyl or dichloride, methyl phosphine dicyclopentadienyl titanium diphenyl or dichloride, methylenedicyclopentadienyl titanium diphenyl or dichloride and other dihalide complexes, and the like; as well as bridged metallocene compounds such as isopropyl(cyclopenta

- 18 -

dienyl)(fluorenyl)zirconium dichloride, isopropyl(cyclopentadienyl)(octahydrofluorenyl)zirconium dichloride
diphenylmethylenecyclopentadienyl)(fluorenyl) zirconium
dichloride, diisopropylmethylenecyclopentadienyl)(fluorenyl)zirconium dichloride, diisobutylmethylenecyclopentadienyl)(fluorenyl) zirconium
dichloride, ditertbutylmethylenecyclopentadienyl)(fluorenyl)zirconium dichloride,
cyclohexylidene(cyclopentadienyl)(fluorenyl) zirconium
dichloride, diisopropylmethylenecyclopentadienyl)(fluorenyl)zirconium
dichloride, isopropyl(cyclopentadienyl)(fluorenyl) hafnium
dichloride, diphenylmethylenecyclopentadienyl)(fluorenyl)hafnium dichloride, diisopropylmethylenecyclopentadienyl)(fluorenyl)hafnium dichloride, diisobutylmethylenecyclopentadienyl)(fluorenyl)hafnium dichloride,
ditertbutylmethylenecyclopentadienyl)(fluorenyl)hafnium dichloride, cyclohexylidene(cyclopentadienyl)(fluorenyl)hafnium dichloride, diisopropylmethylenecyclopentadienyl)(fluorenyl)hafnium
dichloride, isopropyl(cyclopentadienyl)(fluorenyl)titanium
dichloride, diphenylmethylenecyclopentadienyl)(fluorenyl)titanium dichloride, diisopropylmethylenecyclopentadienyl)(fluorenyl)titanium dichloride,
diisobutylmethylenecyclopentadienyl)(fluorenyl)titanium dichloride, ditertbutylmethylenecyclopentadienyl)(fluorenyl)titanium dichloride, cyclohexylidene(cyclopentadienyl)(fluorenyl)titanium dichloride,
diisopropylmethylenecyclopentadienyl)(fluorenyl)titanium dichloride,
racemic-ethylene bis (1-indenyl) zirconium (IV)
dichloride, racemic-ethylene bis (4,5,6,7-tetrahydro-1-indenyl) zirconium (IV) dichloride, racemic-dimethylsilyl

- 19 -

bis (1-indenyl) zirconium (IV) dichloride, racemic-
dimethylsilyl bis (4,5,6,7-tetrahydro-1-indenyl) zirconium
(IV) dichloride, racemic-1,1,2,2- tetramethylsilanylene
bis (1-indenyl) zirconium (IV) dichloride, racemic-
5 1,1,2,2-tetramethylsilanylene bis (4,5,6,7-tetrahydro-1-
indenyl)
zirconium (IV), dichloride, ethylidene (1-indenyl
tetramethylcyclopentadienyl) zirconium (IV) dichloride,
racemic- dimethylsilyl bis (2-methyl-4-t-butyl-1-
10 cyclopentadienyl) zirconium (IV) dichloride, racemic-
ethylene bis (1-indenyl) hafnium (IV) dichloride, racemic-
ethylene bis (4,5,6,7-tetrahydro-1-indenyl) hafnium (IV)
dichloride, racemic-dimethylsilyl bis (1-indenyl) hafnium
(IV) dichloride, racemic-dimethylsilyl (4,5,6,7-
15 tetrahydro-1- indenyl) hafnium (IV) dichloride, racemic-
1,1,2,2-
tetramethylsilanylene bis (1-indenyl) hafnium (IV)
dichloride, racemic-1,1,2,2-tetramethylsilanylene bis
(4,5,6,7-tetrahydro-1- indenyl) hafnium (IV), dichloride,
20 ethylidene (1-indenyl-2,3,4,5-tetramethyl-1-
cyclopentadienyl) hafnium (IV) dichloride, racemic-
ethylene bis (1-indenyl) titanium (IV) dichloride,
racemic-ethylene bis (4,5,6,7-tetrahydro-1-indenyl)
titanium (IV) dichloride, racemic- dimethylsilyl bis (1-
25 indenyl) titanium (IV) dichloride, racemic- dimethylsilyl
bis (4,5,6,7-tetrahydro-1-indenyl) titanium (IV)
dichloride, racemic-1,1,2,2-tetramethylsilanylene bis (1-
indenyl) titanium (IV) dichloride racemic-1,1,2,2-
tetramethylsilanylene bis (4,5,6,7-tetrahydro-1-
30 indenyl) titanium (IV) dichloride, and ethylidene (1-
indenyl-2,3,4,5-tetramethyl-1-cyclopentadienyl) titanium
IV) dichloride.

- 20 -

Preferred metallocenes are bis(cyclopentadienyl)titanium dimethyl, isopropyl (cyclopentadienyl) fluoroenyl)zirconium dimethyl, bis (1-indenyl) zirconium (IV) dimethyl, (4,5,6,7-tetrahydro-1-indenyl)hafnium(IV)dimethyl, dimethylzirconene, 5 dimethylethylenebisindenylzirconium, and dimethylethylene bis(tetrahydroindenyl)zirconium.

The transition metal catalyst useful in this invention can include non-cyclopentadienyl catalyst 10 components (such as pentadienyls) as well as ancillary ligands such as borollides or carbollides in combination with a transition metal.

Transition metal catalyst also include traditional Ziegler-Natta ("ZN") catalysts precursor which are by the 15 formula M^aR_a , wherein M^a is a transitional metal from the Group 3 through 10 and the Lanthanide Series in the Periodic Table, wherein "a" is its valence state and the number of R's is equal to "a" and each may be the same or different and independently selected from the group 20 consisting of halogens(preferably Cl and Br), alkyls(preferably C1-C20; more preferably ethyl, butyl, octyl and ethylhexyl), alkoxys (preferably C1-C20, more preferably ethoxy, isopropoxy, butoxy and phenoxy), aryls (preferably C6-C20(including substituted aryls), more 25 preferably phenyl, p-tolyl, benzyl, 4-t-butylphenyl, 2,6 dimethylphenyl, 3,5- methylphenyl, 2,4-dimethylphenyl, 2,3-dimethylphenyl groups) and mixtures thereof. For example, $TiCl_4$, $TiCl_3$, $VOCl_3$, VCl_4 , $TiPhenyl_4$, $V(OButyl)_3$, tetramethyl zirconium, tetrabenzylzirconium, 30 tetramethoxyzirconium, tetraethoxyzirconium, tetrabutoxyzirconium, bis(2,5-di-t-butylphenoxy)dimethylzirconium, bis(2,5-di-t-

- 21 -

butylphenoxy)dichlorozirconium and zirconium
bis(acetylacetonate), tetramethyl titanium,
tetrabenzyltitanium, tetramethoxytitanium,
tetraethoxytitanium, tetrabutoxytitanium, bis(2,5-di-t-
5 butylphenoxy)dimethyltitanium, bis(2,5-di-t-
butylphenoxy)dichlorotitanium and titanium
bis(acetylacetonate).

The activator of the present invention is preferably
10 used with a metallocene catalyst precursor defined above.

It is the combination of the activator and the catalyst
precursor that forms the active catalyst. The amount of
the present support activator used with a transition metal
catalyst precursor is an amount sufficient to provide a
15 molar ratio of the support M, as defined above from
reagent MR_x , to the transition metal in the catalyst
ranging from 1:1 to 1:5, preferably 1:1.

POLYMERIZATION

20 The supported catalytic activator according to the
present invention can be used in any polymerization
technique. Methods and apparatus for effecting such
polymerization reactions are well known. The supported
catalytic activators according to the present invention
25 can be used in similar amounts and under similar
conditions to known olefin polymerization catalysts
systems.

As used herein, "Polymerization" includes
copolymerization and terpolymerization and the terms
30 olefins and olefinic monomer includes olefins, alpha-
olefins, diolefins, strained cyclic, styrenic monomers,
acetylenically unsaturated monomers, cyclic olefins alone

- 22 -

or in combination with other unsaturated monomers. While the catalyst system of the present invention is active for this broad range of olefinic monomer feedstock, alpha-olefins polymerizations is preferred, especially the homopolymerization of ethylene or the
5 copolymerization of ethylene with olefins having 3 to 10 carbon atoms.

10

"Polymerization techniques" for olefin polymerization according the present invention can be solution polymerization, slurry polymerization or gas phase polymerization techniques. Method and apparatus
15 for effecting such polymerization reactions are well known and described in, for example, Encyclopedia of Polymer Science and Engineering published by John Wiley and Sons, 1987, Volume 7, pages 480-488 and 1988, Volume 12, pages 504-541. The catalyst according to the present
20 invention can be used in similar amounts and under similar conditions to known olefin polymerization catalyst.

Typically, for the slurry process, the temperature is from approximately 0 degrees C to just below the
25 temperature at which the polymer becomes swollen in the polymerization medium. For the gas phase process, the temperature is from approximately 0 degrees C to just below the melting point of the polymer. For the solution process, the temperature is typically the temperature
30 from which the polymer is soluble in the reaction medium up to approximately 320 degrees C.

- 23 -

The pressure used can be selected from a relatively wide range of suitable pressures, e.g., from subatmospheric to about 350 Mpa. Suitably, the pressure is from atmospheric to about 6.9 Mpa, or 0.05-10 MPa, especially 0.14-5.5 Mpa. Pressure is dictated by the process and the desired product. In the slurry or particle form process, the process is suitably performed with a liquid inert diluent such as a saturated aliphatic hydrocarbon. Suitably the hydrocarbon is a C₄ to C₁₀ hydrocarbon, e.g., isobutane or an aromatic hydrocarbon liquid such as benzene, toluene or xylene. The polymer is recovered directly from the gas phase process or by filtration or evaporation from the slurry process or evaporation from the solution process.

The supported activator of the present invention are particularly suited for the gas phase or slurry processes.

DESCRIPTION OF THE DRAWINGS

Figure 1 is a depiction of the ¹¹B Magnetic angle spinning (MAS) Nuclear Magnetic Resonance (NMR) spectrum of [B(C₆F₅)₃] physisorbed on a calcined amorphous silica gel (Trace A) and a depiction of the ¹¹B MAS NMR of a supported catalytic activator as prepared in Example 1, described below, and depicts the direct chemical bond of the [B(C₆F₅)₃] to the oxygen of the amorphous silica gel (Trace B).

The sharp line pattern in Trace B is indicative of a four coordinate boron center, proving [B(C₆F₅)₃] has reacted chemically with the silica to form a four coordinate borate salt.

- 24 -

EXAMPLES

The following examples are provided to illustrate the present invention, but are not to be construed as limiting the invention in any way except as provided in the appended claims. All parts and percentages are by weight unless otherwise indicated.

Example 1.

Preparation of Supported Borate A. Davison Grade 948 silica, a 50 micron average particle size spheroidal silica gel, was calcined in air at 500°C for 4 hours, then transferred to an argon-filled glove box. To a slurry of 5.02 g silica in 50 ml heptane was added 0.5 ml of a 2 Molar solution of $n\text{BuLi}$ in hexane. After 30 minutes, 0.518 g of $[\text{B}(\text{C}_6\text{F}_5)_3]$ was added. The mixture was stirred for 1 hour, and 0.281 g of Ph_3CCl was introduced. The slurry immediately turned yellow, then darkened to orange over the course of 10 minutes. After 30 minutes, the orange solid was collected on a fitted funnel, washed with toluene and pentane, and dried in vacuo. The solid was analyzed by ^{11}B NMR, which confirmed formation of four-coordinate borate species.

Example 2.

Preparation of Supported Borate B. The same procedure as reported for Borate A was followed with the following reagents: 2.640 g SRA alumina, 0.25 ml $n\text{BuLi}$, 0.26 g $[\text{B}(\text{C}_6\text{F}_5)_3]$, and 0.141g Ph_3CCl . The isolated product was a pale brown solid. The solid was analyzed by ^{11}B NMR, which confirmed formation of four-coordinate borate species.

Example 3.

Preparation of Supported Borate C. To 10.0 g Davison 948 silica in 200 ml heptane were added 10 mmol of a heptane solution of $[\text{B}(\text{C}_6\text{F}_5)_3]$ and 1.3 ml of dimethylaniline. The

- 25 -

solution was heated at reflux for 4 hours, yielding a white solid and a blue filtrate. The solid was analyzed by ^{11}B NMR, which confirmed formation of four-coordinate borate species.

5 Example 4.

Preparation of Polyolefin Catalyst A. 0.245 g Borate A was added to a solution of 0.5 ml of a triethyl aluminum solution (5.6 % Al in heptane) in 50 ml heptane. To the mixture was added 0.0020 g Cp_2ZrMe_2 . The resulting mixture
10 was heated to 45°C, and 53 psi ethylene was introduced. Polymerization yielded 3.96 g free-flowing polyethylene in 34 minutes, corresponding to an activity of 895 gPE/mmol Zr/hr.

Example 5.

15 Preparation of Polyolefin Catalyst B. As above, except 0.150 g borate B, 0.0015 g Cp_2ZrMe_2 were employed. The catalyst yield 1.95 g polyethylene in 23 minutes, corresponding to an activity of 835 gPE/mmol Zr/hr.

Example 6.

20 Preparation of Polyolefin Catalyst C. 1 g of Borate C was slurried in 500 ml heptane, and 1 mmol triethylaluminum was added as a heptane solution. To this mixture was added 0.01 g Cp_2ZrMe_2 . Polymerization at 35 psi ethylene and 40°C yielded 6 g polyethylene in 0.25 hr, corresponding to an
25 activity of 290 gPE/mmolZr/Hr.

- 26 -

We claim:

1. A supported catalyst activator, comprising a four coordinate anion with a direct chemical bond to a catalyst support, wherein said anion species is comprised of a neutral, three coordinate compound, MR_3 , and a support having oxygen containing functionalities, wherein
- M is selected from the group comprising boron, tellurium, aluminum, gallium, indium and mixtures thereof;
- R's can be the same or different and are selected from the group comprising alkyls, alkoxys, alkenyls, halo-substituted alkyls, alkoxys and alkenyls, aryls, aryl halides, alkoxy and halides and mixtures thereof; and
- a cation counter ion to said anion, wherein said cation is a protonated base or a Lewis Acid capable of protonating or abstracting a moiety from a transition metal containing catalyst precursor resulting in a cationic transition metal species.

- 27 -

2. The supported catalyst activator of claim 1,
wherein the M is boron, aluminum or mixtures thereof;

the support is selected from the group comprising
SiO₂, Al₂O₃, MgO, ZrO₂, TiO₂, Fe₂O₃, B₂O₃, CaO, ZnO, BaO, ThO,
5 and aluminum phosphate gel materials and mixtures
thereof;

R's can be the same or different and are selected
from the group comprising halosubstituted and
nonsubstituted C1-C5 alkyls, C6-C18 aryls and mixtures
10 thereof; and


the cation is selected from the group comprising
ammonium salts, carboniums, phosphoniums, carbenium,
oxoniums, tropylium, ferroceniums, silver and mixtures
thereof.

15

3. The supported activator according to claim 1,
wherein the M is boron, R is pentafluorophenyl, the
support is selected from the group comprising silica,
silica alumina, silica alumina titania, silica maganesium
20 chloride, silica titania, aluminium phosphate gel,
zeolite, ferrite and mixtures thereof and the cation is
selected from the group comprising N,N-dimethylanilinium,
triphenylcarbenium and mixtures thereof.

- 28 -

4. A supported catalytic activator comprising a compound of the general formula:



5

Wherein, $[C]^+$ is an activating cation, which may be a Bronsted acid capable of donating a proton to the transition metal catalytic precursor resulting in a transition metal cation or an abstracting moiety that is capable of reacting with a transition metal catalytic precursor resulting in the cationic transition metal species and mixtures thereof;

10 R can be the same or independent and are selected from the group comprising halogens, mono or multi-cyclic aryls, alkyls, alkoxys, and alkenyl compounds, and halosubstituted mono or multi-cyclic aryls, alkyls, alkoxys, and alkenyls compounds and mixtures thereof;

15 M is selected from the group comprising boron, aluminum, gallium, indium, tellurium and mixtures thereof;

20 O is oxygen; and

Support is selected from the group of inorganic carriers, inorganic oxide carriers, and organic carriers.

- 29 -

5. The supported catalytic activator of claim 4, wherein:

C' is selected from the group comprising ammoniums of methylamine, aniline, dimethylamine, diethylamine, N-methylaniline, diphenylamine, trimethylamine, triethylamine, N,N-dimethylaniline, methyldiphenylamine, pyridine, p-bromo-N,N,-dimethylaniline, p-nitro-N,N-dimethylaniline; phosphoniums from triethylphosphine, triphenylphosphine and diphenylphosphine; oxoniums from dimethyl ether, diethyl ether tetrahydrofuran and dioxane; sulfoniums from thioethers such as diethyl thioethers and tetrahydrothiophene; silver, tropylium, carbeniums, ferroceniums and mixtures thereof and mixtures of two or more of the foregoing;

R's are the same or different and are selected from comprising chlorine, bromine, and halosubstituted and nonsubstituted C1-C20 alkenyls, C1-C20 alkyls, C6-C20 aryls, C1-C20 alkoxy and mixtures thereof;

M is selected from the group comprising boron, aluminium and mixtures thereof; and

Support is selected from the group comprising SiO₂, Al₂O₃, MgO, ZrO₂, TiO₂, Fe₂O₃, B₂O₃, CaO, ZnO, BaO, ThO, and aluminum phosphate gel materials and mixtures thereof.

- 30 -

6. The supported activator of claim 5, wherein the C⁺ is N,N-dimethylanilinium, triphenylcarbenium, and mixtures thereof;

R's are the same or different and are selected from
5 the group comprising chlorine, bromine, and
halosubstituted and nonsubstituted ethenyl, propylenyl,
butenyl, pentenyl, methyl, ethyl, n-propyl, iso-propyl,
n-butyl, n-octyl, and 2-ethylhexyl, phenyl, p-tolyl,
benzyl, 4-t-butylphenyl, 2,6 dimethylphenyl,
10 pentafluorophenyl, 3,5- methylphenyl, 2,4-dimethylphenyl,
2,3-dimethylphenyl, pentafluorobenzyl, naphthyl, ethoxy,
butoxy, t-butoxy, n-butoxy and mixtures thereof; and

Support is selected from the group comprising silica,
silica alumina, silica alumina titania, silica maganesium
15 chloride, silica titania, aluminium phosphate gel,
zeolite, ferrite and mixtures thereof.

- 31 -

7. A method for preparing a supported catalyst activator comprising an anion chemically bound to a catalyst support having oxygen functionalities on the surface, said method comprising:

- 5 1) treating a catalyst support with a C1-C20 metal alkyl, C6-C20 metal aryl, substituted C1-C20 metal alkyls and aryls and mixtures thereof, and where the metal in this reagent is selected from the group comprising Group 1 and 2 metals
10 from the Periodic table and mixtures thereof, wherein such reagent can react with the support surface to generate nucleophilic oxygen sites;
- 15 2) adding a neutral, three coordinate metal component, MR_3 , wherein the M is selected from the group comprising of boron, tellurium, aluminum, gallium and indium and mixtures thereof and the R's are the same or different and are selected from the group consisting of
20 halogens, mono or multi-cyclic aryls, alkyls, alkoxys and alkenyl compounds and halosubstituted mono or multi-cyclic aryls, alkoxys alkyls, and alkenyl compounds mixtures thereof;
- 25 3) adding an organic compound of the selected from the group represented by the formula $R'X$ wherein the R' is selected from the group of hydrogen, alkenyl, alkyl, aryl or arylalkyl radical having from 1-20 carbons or two carbon atoms joined together to form a C4 to C6 ring,
30 and X is any halogen; pronated amides, ammonium and mixtures thereof.

- 32 -

8. The method according to claim 7, wherein the method further comprises a support that is selected from the group comprising SiO_2 , Al_2O_3 , MgO , ZrO_2 , TiO_2 , Fe_2O_3 , B_2O_3 , CaO , ZnO , BaO , ThO , and aluminum phosphate gel materials and mixtures thereof;

the metal containing reagent of step 1) is selected from the group comprising N-butyllithium, dibutylmagnesium, methyllithium, butylmagnesium chloride and mixture thereof;

the MR_3 of step 2) is selected from the group comprising tri(phenyl)boron, tri(p-tolyl)boron, tri(o-tolyl)boron, tri(pentafluorophenyl)boron, tri(o,p-dimethylphenyl)boron, tri(m,m-di(trifluoromethyl)phenyl)boron, tri(p-trifluoromethylphenyl)boron, tri(phenyl)aluminum, tri(p-tolyl)aluminum, tri(o-tolyl)aluminum, tri(pentafluorophenyl)aluminum, tri(o,p-dimethylphenyl)aluminum, tri(m,m-di(trifluoromethyl)phenyl)aluminum, tri(p-trifluoromethylphenyl) aluminum, and the like; and mixtures of the foregoing; and

the organic compound in step 3) is selected from the group comprising chlorotriphenylmethane, dimethylanilinium chloride and mixtures thereof.

- 33 -

9. A method for preparing a supported catalyst activator, comprising an anion species chemically bound to a catalyst support, said method comprising:

- 5 1) treating a catalyst support with an organic base in solution, and
- 2) adding a neutral material, MR_x , wherein the M is selected from the group comprising boron, tellurium, aluminum, gallium, indium and mixtures thereof, and the R's are the same or
10 different and selected from the group comprising halogens, alkyls, alkenyls, alkoxyls, halogen substituted alkyls, alkoxyls and alkenyls, aryl, aryl halides, and mixtures thereof.

- 15 10. The method according to claim 9, wherein the method further comprises an organic base in step 1) that is an organic base having the general formula having the formula RN_x , wherein the N is nitrogen and the R's are independently selected from the group comprising hydrogen,
20 alkyl, aryls, substituted alkyls and aryls, and may be the same or different; and

 the Support is selected from the group comprising SiO_2 , Al_2O_3 , MgO , ZrO_2 , TiO_2 , Fe_2O_3 , B_2O_3 , CaO , ZnO , BaO , ThO , and aluminum phosphate gel materials and mixtures
25 thereof.

11. The method according to claim 10, wherein the method further comprises an organic base in step 1) is selected from the group comprising dimethylaniline, tributylamine, triethylamine and mixtures thereof.
30

- 34 -

12. An activated catalyst composition comprising the supported catalyst activator according to claim 1 and at least one cationic transition metal species derived from one or more stabilized transition metal compounds.

5

13. An activated catalyst composition comprising the supported catalyst activator according to claim 2 and at least one cationic transition metal species derived from one or more stabilized transition metal compounds.

10

14. An activated catalyst composition comprising the supported catalyst activator according to claim 3 and at least one cationic transition metal species derived from one or more stabilized transition metal compounds.

15

15. An activated catalyst composition comprising the supported catalyst activator according to claim 4 and at least one cationic transition metal species derived from one or more stabilized transition metal compounds.

20

16. An activated catalyst composition comprising the supported catalyst activator according to claim 5 and at least one cationic transition metal species derived from one or more stabilized transition metal compounds.

25

17. An activated catalyst composition comprising the supported catalyst activator according to claim 6 and at least one cationic transition metal species derived from one or more stabilized transition metal compounds.

30

18. The composition according to claims 12-17, wherein the cationic transition metal species is derived

- 35 -

from a metallocene, Ziegler-Natta compounds and mixtures thereof.

19. The composition according to claim 12-17,
5 wherein the cationic transition metal species contains a
metal selected from the group comprising titanium,
hafnium, zirconium and mixtures thereof.

20. A process for polymerizing olefinic monomer
10 material comprising contacting at least one olefinic
monomer with at least one catalyst activator defined by
claims 1-12, in the presence of at least one olefin
catalytic transition metal precursor in a reaction zone at
a temperature and for a time sufficient to polymerize at
15 least a portion of the olefin to a polyolefin.

- 36 -

21. The process according to claim 20, wherein the catalytic precursor is selected from the group comprising bis(cyclopenta-dienyl)titanium dimethyl, isopropyl(cyclopentadienyl)fluoroenyl)zirconium dimethyl, bis (1-indenyl) zirconium (IV) dimethyl, (4,5,6,7-tetrahydro-1-indenyl)hafnium(IV)dimethyl, dimethylzirconene, dimethylethylenebisindenylzirconium, and dimethylethylene bis(tetrahydroindenyl)zirconium, phenyl, p-tolyl, benzyl, 4-t-butylphenyl, 2,6 dimethylphenyl, 3,5- methylphenyl, 2,4-dimethylphenyl, 2,3-dimethylphenyl groups) and mixtures thereof. For example, $TiCl_4$, $TiCl_3$, $VOCl_3$, VCl_3 , $TiPhenyl_4$, $V(OButyl)_3$, tetramethyl zirconium, tetrabenzylzirconium, tetramethoxyzirconium, tetraethoxyzirconium, tetrabutoxyzirconium, bis(2,5-di-t-butylphenoxy)dimethylzirconium, bis(2,5-di-t-butylphenoxy)dichlorozirconium and zirconium bis(acetylacetonate), tetramethyl titanium, tetrabenzyltitanium, tetramethoxytitanium, tetraethoxytitanium, tetrabutoxytitanium, bis(2,5-di-t-butylphenoxy)dimethyltitanium, bis(2,5-di-t-butylphenoxy)dichlorotitanium and titanium bis(acetylacetonate) and mixtures thereof.


25

22. The process according to claim 20, wherein the reaction zone occurs in a slurry, solvent or gas phase polymerization reactor.

- 37 -

23. A polymer formed by polymerizing olefinic monomer material in the presence of at least one catalyst activator according to claims 1-12 and at least one olefin catalyst.

1 / 1



INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 96/00644

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08F4/60 C08F10/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO,A,93 11172 (EXXON CHEMICAL PATENTS INC) 10 June 1993 cited in the application see page 18, lines 21-22, and page 37, line 20 to page 38, line 14 ---	1-6, 12-23
A	WO,A,91 09882 (EXXON CHEMICAL PATENTS INC) 11 July 1991 see claim 9; page 16, line 9 to page 17, line 14; page 22, lines 20-30; examples 10, 12, 14 ---	1-23
A	WO,A,94 03506 (EXXON CHEMICAL PATENTS INC) 17 February 1994 cited in the application see page 5, lines 33-35, and page 23, lines 6-14 ---	1-23

	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *A* document member of the same patent family

Date of the actual completion of the international search

29 May 1996

Date of mailing of the international search report

12.06.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Mergoni, M

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 96/00644

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	<p>WO,A,96 04319 (EXXON CHEMICAL PATENTS INC ;WALZER JOHN FLEXER JR (US)) 15 February 1996 see claims</p> <p>-----</p>	1-23

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 96/00644

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
WO-A-9311172	10-06-93	CA-A-	2124187	10-06-93
		EP-A-	0614468	14-09-94
		JP-T-	7501573	16-02-95
		US-A-	5427991	27-06-95

WO-A-9109882	11-07-91	AT-T-	122688	15-06-95
		AU-B-	643255	11-11-93
		AU-B-	7181191	24-07-91
		CA-A-	2072752	03-07-91
		DE-D-	69019535	22-06-95
		DE-T-	69019535	19-10-95
		EP-A-	0507876	14-10-92
		EP-A-	0627448	07-12-94
ES-T-	2072598	16-07-95		

WO-A-9403506	17-02-94	CA-A-	2141814	17-02-94
		EP-A-	0702700	27-03-96
		JP-T-	7509752	26-10-95

WO-A-9604319	15-02-96	AU-B-	3204695	04-03-96
